

SYNTHESIS OF MOLTEN SALT AS HEAT TRANSFER FLUID FOR WASTE
HEAT RECOVERY APPLICATION

NURUL ADILA BINTI MOHAMAD REDZUAN

A thesis submitted in fulfillment of the requirement for the award of the Degree of
Master of Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering
Universiti Tun Hussein Onn Malaysia

JUNE 2015

This thesis dedicated to my parents

MARIAM BT IBRAHIM and MOHAMAD REDZUAN BIN WAN NGAH,

*For their endless love, support and encouragement...may ALLAH grace and bounty
be upon them...*

To all my siblings..

Yie, Kak Syifa, Ya and Mimi..

Thanks for your support and prayers..



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

ACKNOWLEDGEMENT

In the name of Allah, the Most Gracious and the Most Merciful.

Alhamdulillah, all praises to Allah for the strengths and His blessing in completing this thesis. Special appreciation goes to my supervisor, Dr Wan Nur Azrina Binti Wan Muhammad, for her supervision and constant support. Her invaluable help of constructive comments and suggestions throughout the experimental and thesis works have contributed to the success of this research.

Sincere thanks to all my friends especially Husna, Amalina, Haslinda and Mardhati also others for their kindness and moral support during my study. Thanks for the friendship and memories.

Last but not least, my deepest gratitude goes to my beloved parents; Mr. Mohamad Redzuan Bin Wan Ngah and Mrs. Mariam Binti Ibrahim and also to my siblings and sister-in-law for their endless love, prayers and encouragement. Also not forgetting to those who indirectly contributed in this research, your kindness means a lot to me. Thank you very much

Nurul Adila Mohamad Redzuan

June 2015

ABSTRACT

Basically, various materials such as water, oil heat, ionic liquids and also molten salt are selected to serve as heat transfer fluid. The properties of the different heat transfer fluid determine their performance in any application. The development of nitrate molten salt with different constituent salt are studied to characterize the physical and thermal properties based on low melting point and high thermal stability in order to be considered as heat transfer fluid in waste heat recovery applications. The nitrate based molten salt that has been use in this study consists of binary, ternary and quaternary salt mixture with different weight composition. Molten salt mixture has been dried in the furnace for 12 hours before mixing. After mixing, the salt mixture was heated in furnace at 150 °C for 4 hours and increased the temperature to 400 °C for 8 hours for homogenize the salt mixture. The temperature was reduced to 115 °C for 1 hour before removed from furnace. Thermal analyses were performed using differential thermal analysis (DTA), thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC). These analyses were conducted to obtain the melting point, thermal stability and heat capacity of molten salt and fulfill the targeted characteristic of a heat transfer fluid. The result shows the melting point for ternary and quaternary mixtures are closely 100 °C where the value is 92.4 °C and 98.9 °C compared than binary mixtures. Thermal stability analyzed in this study shows that the value for all mixture above 500 °C but quaternary mixture showed the highest thermal stability which the value is 701 °C. For heat capacity value of all mixture shows a range between 2.5 – 4.7 J/g °C and quaternary mixture showed the highest value of heat capacity when compared to all mixture with value of 4.7 J/g °C. For the conclusion, the quaternary salt mixture has fulfilled the targeted characteristic as heat transfer fluid with low melting point, high thermal stability and heat capacity.

ABSTRAK

Pelbagai bahan telah dipilih untuk bertindak sebagai cecair pemindahan haba seperti air, minyak, cecair ionik dan juga garam lebur. Perbezaan pada ciri –ciri bahan tersebut yang menentukan prestasi bahan dalam sebarang aplikasi. Pembangunan garam lebur berasaskan nitrat dengan konstituen yang berbeza dikaji untuk mencirikan sifat fizikal dan termal bagi mendapatkan takat lebur yang rendah serta kestabilan termal yang tinggi untuk dipertimbangkan sebagai cecair pemindahan haba sebagai aplikasi sisa pemulihan haba. Garam lebur berasaskan nitrat yang digunakan terdiri daripada campuran garam binari, ternari dan quaternari dengan komposisi yang berbeza. Campuran garam lebur akan dikeringkan di dalam relau selama 12 jam sebelum proses campuran berlaku. Selepas pencampuran, garam akan dipanaskan dalam relau pada suhu 150 °C selama 4 jam dan dinaikkan pada 400 °C selama 8 jam bagi menyeragamkan campuran. Suhu akan dikurangkan pada 115 °C selama satu jam sebelum dikeluarkan dari relau. Analisis terma yang telah dijalankan adalah *differential thermal analysis* (DTA), *thermogravimetric analysis* (TGA) dan *differential scanning calorimetry* (DSC) bagi mendapatkan nilai takat lebur, kestabilan terma dan kapasiti haba. Keputusan menunjukkan takat lebur bagi campuran ternari dan quaternari menghampiri 100 °C dengan nilai 92.4 °C dan 98.9 °C berbanding dengan campuran binari. Analisis kestabilan terma menunjukkan nilai bagi semua campuran melebihi 500 °C namun campuran quaternari mempunyai nilai kestabilan termal yang paling tinggi iaitu 701 °C. Untuk nilai kapasiti haba pula semua campuran menunjukkan julat nilai antara 2.5 – 4.7 J/g °C dan campuran quaternari adalah yang paling tinggi. Campuran quaternari telah memenuhi ciri cecair pemindahan haba dengan takatlebur yang rendah, kestabilan termal dan kapasiti haba yang tinggi.

CONTENTS

	TITLE	i
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENT	iv
	ABSTRACT	v
	CONTENT	vii
	LIST OF TABLES	ix
	LIST OF FIGURES	
	LIST OF SYMBOLS	
CHAPTER 1	INTRODUCTION	1
1.1	Background of Study	1
1.2	Problem of Statement	2
1.3	Objective	3
1.4	Scope of Study	3
CHAPTER 2	LITERATURE REVIEWS	5
2.1	Introduction	5
2.2	Overview of molten salt and applications	6
2.3	Melting Point	8
2.3.1	Melting point for various salt	8
2.3.2	Melting temperature for molten salt based on nitrate/nitrite system	10
2.4	Heat capacity	11
2.4.1	Heat Capacity for various salt	12
2.5	Thermal stability for various salt	13
2.6	State of the art alkali nitrate/nitrite salt mixtures	15
2.7	Eutectic mixture	15
2.7.1	Binary mixture	16

2.7.2	Ternary mixture	18
2.7.3	Quaternary mixture	21
2.8	Performance molten salt as heat transfer	23
2.9	Molten Salt as heat carrier in heat recovery system	23
CHAPTER 3	METHODOLOGY	26
3.1	Introduction	26
3.2	Preparation of Molten Salt	28
3.3	Eutectic Mixture	28
3.4	Characterize Physical and Thermal Properties	30
3.4.1	Heat Capacities	30-
3.4.2	Thermal Stability	31
3.4.3	Melting Point	32
CHAPTER 4	RESULT AND DISCUSSION	33
4.1	Introduction	33
4.2	Melting point determination	33
4.2.1	Binary mixture	33
4.2.2	Ternary mixture	36
4.2.3	Quaternary mixture	38
4.3	Melting point for all system mixture	39
4.4	Thermal stability determination	40
4.4.1	Result of thermal stability	40
4.4.2	Discussion of thermal stability determination	43
4.5	Heat capacity determination	45
4.5.1	Discussion of heat capacity determination	51
CHAPTER 5	CONCLUSION AND RECOMMENDATION	53
5.1	Conclusion	53
5.2	Recommendation	54
REFERENCES		56
APPENDIX		
	TGA result	
	DSC result	
	Gantt Chart	

LIST OF TABLES

2.1	Melting point of various nitrate salt systems	9
2.2	Melting point of various carbonate salt systems	10
2.3	Melting point of various fluoride/chloride salt systems.	10
2.4	Matrix of (minimum) melting temperature of subsystems of the reciprocal system Ca,K,Li,Na//NO ₂ ,NO ₃	11
2.5	Heat capacity of various nitrate salt systems	12
2.6	Heat capacity of various carbonate salt systems	13
2.7	Heat capacity of various fluoride/chloride salt systems	13
2.8	Overview of alkali nitrate/nitrite salt mixture	15
2.9	The melting temperature and thermal stability of LiNO ₃ - NaNO ₃ -KNO ₃ ternary system with different composition	20
2.10	Literature review of the minimum melting temperature and composition of the system Ca(NO ₃) ₂ -KNO ₃ -NaNO ₃	21
4.1	Specific heat value of 46 wt% NaNO ₃ -54 wt% KNO ₃	46
4.2	Specific heat value of 54.2 wt% LiNO ₃ -45.8 wt% NaNO ₃	47
4.3	Specific heat value 56.4 wt% KNO ₃ -19.6 wt% LiNO ₃ - 24.1 wt% NaNO ₂	48
4.4	Specific heat value 13.5 wt% LiNO ₃ - 67.2 wt% KNO ₃ -19.3 wt% Ca(NO ₃) ₂	49
4.5	Specific heat value 20 wt% LiNO ₃ - 40wt% KNO ₃ -25 wt% Ca(NO ₃) ₂ -15 wt% NaNO ₃	50

LIST OF FIGURES

2.1	Molten salt system	8
2.2	TGA measurement of single alkali nitrate salts and alkali nitrite salt and salt mixture	14
2.3	Published phase diagrams for the a) $\text{NaNO}_3\text{-Na}_2\text{CO}_3$ and b) $\text{KNO}_3\text{-K}_2\text{CO}_3$	14
2.4	Overview of different phase diagrams of the system $\text{KNO}_3\text{-NaNO}_3$	17
2.5	Phase diagrams of the system $\text{LiNO}_3\text{-NaNO}_3$	18
2.6	Heat capacity data plot of $\text{LiNO}_3\text{-NaNO}_3\text{-KNO}_3$ ternary system	19
2.7	$\text{Ca(NO}_3)_2\text{-KNO}_3\text{-NaNO}_3$ ternary diagram	20
2.8	Thermal decomposition curve of $\text{LiNO}_3\text{-Ca(NO}_3)_2\text{-NaNO}_3\text{-KNO}_3$ mixture	22
3.1	Flow chart for synthesis molten salt as heat transfer fluid	27
3.2	Component of molten salt	28
3.3	Molten salt after mixture for binary system a) $\text{KNO}_3 + \text{NaNO}_3$ b) $\text{LiNO}_3 + \text{KNO}_3$	29
3.4	Molten salt after mixture for ternary system a) $\text{LiNO}_3 + \text{KNO}_3 + \text{NaNO}_2$ b) $\text{LiNO}_3 + \text{KNO}_3 + \text{Ca(NO}_3)_2$	29
3.5	Molten salt after mixture for ternary system $\text{LiNO}_3 + \text{KNO}_3 + \text{Ca(NO}_3)_2 + \text{NaNO}_3$	30
3.6	Differential scanning calorimetry (DSC)	31
3.7	Thermal gravimetric analysis (TGA)	31
3.8	Differential Thermal Analysis (DTA)	32
4.1	DTA curve for salt mixture of 46 wt% $\text{NaNO}_3\text{-54 wt% KNO}_3$.	34
4.2	DTA curve for salt mixture of 45.8 wt% $\text{NaNO}_3\text{-54.2 wt% LiNO}_3$	35

4.3	DTA curve for salt mixture of 24.1 wt% NaNO_2 -56.4 wt% KNO_3 -19.6 wt% LiNO_3	36
4.4	DTA curve for salt mixture 19.3 wt% $\text{Ca}(\text{NO}_3)_2$ -67.2 wt% KNO_3 -13.5 wt% LiNO_3	37
4.5	DTA curve for salt mixture 15 wt% NaNO_3 -40 wt% KNO_3 -20 wt% LiNO_3 -25 wt% $\text{Ca}(\text{NO}_3)_2$	38
4.6	Melting point for all system in $^\circ\text{C}$	39
4.7	TG curve for salt mixture of 46 wt% NaNO_3 -54 wt% KNO_3	40
4.8	TG curve for salt mixture of 45.8 wt% NaNO_3 -54.2 wt% LiNO_3	41
4.9	TG curve of salt mixture 24.1 wt% NaNO_2 -56.4 wt% KNO_3 -19.6 wt% LiNO_3	41
4.10	TG curve of salt mixture 19.3 wt% $\text{Ca}(\text{NO}_3)_2$ -67.2 wt% KNO_3 -13.5 wt% LiNO_3	42
4.11	TG curve of salt mixture 15 wt% NaNO_3 -40 wt% KNO_3 -20 wt% LiNO_3 -25 wt% $\text{Ca}(\text{NO}_3)_2$	42
4.12	Thermal stability and decomposition temperature for all system in $^\circ\text{C}$	43
4.13	DSC plot of 46 wt% NaNO_3 -54 wt% KNO_3	46
4.14	DSC plot of 54.2 wt% LiNO_3 -45.8 wt% NaNO_3	47
4.15	DSC plot of 56.4 wt% KNO_3 -19.6 wt% LiNO_3 - 24.1 wt% NaNO_2	48
4.16	DSC plot of 13.5 wt% LiNO_3 - 67.2 wt% KNO_3 -19.3 wt% $\text{Ca}(\text{NO}_3)_2$	49
4.17	DSC plot of 20 wt% LiNO_3 - 40wt% KNO_3 -25 wt% $\text{Ca}(\text{NO}_3)_2$ -15 wt% NaNO_3	50
4.18	Heat capacity value for all salt mixture in J/g $^\circ\text{C}$	51

LIST OF SYMBOLS

$^{\circ}\text{C}$	-	Celcius
%	-	Percent
NaNO_3	-	Sodium Nitrate
NaNO_2	-	Sodium Nitrite
KNO_3	-	Potassium Nitrate
$\text{Ca}(\text{NO}_3)_2$	-	Calcium Nitrate
LiNO_3	-	Lithium Nitrate
HTF	-	Heat Transfer Fluid
TES	-	Thermal Energy Storage
STP	-	Standard Temperature and Pressure



PTTA
PERPUSTAKAAN TUNKU TUN AMINAH

CHAPTER 1

Introduction

1.1 Background of study

Renewable energy sources such as wind, solar, water power, geothermal and biomass are playing more and more significant role in our energy supply. It is because the cheap cost and infinite amount of energy storage inside the resources. Besides that, solar energy is emphasized since 20th century and viewed as promising alternative method to satisfy the large energy consumption every day in the world. Various materials are selected to serve as energy heating fluid such as water, oil heat, ionic liquids and molten salt. The properties of the different heat transfer fluid determine the performance of solar energy systems. Considering various physical and chemical characteristics relative heat energy storage system, molten salt has been proposed as a group that is suitable for a wide range of application temperature. They are emphasized in the application of solar energy because of a low melting point and high upper limit which can increase the stable working range.

Molten salt is defined as salt that is in solid state at standard temperature and pressure, (STP) but due to high temperature molten salt categorized as a liquid phase. The molten salt is usually in liquid form even at STP and is also known as ionic liquids. This molten salt has a variety of uses depending on the application used. Molten salts have been used in many industries as a high temperature heat transfer medium. For this research it is more focused to the molten salts that can be used as heat transfer fluid as well as for heat recovery system. Before molten salt was selected as the best, various solvents have been used as experimental materials including water, air, oil and sodium. Molten salt is used because it is a liquid at atmospheric pressure, non-flammable, low cost and efficient in store energy

(Jagadees, 2011). This paper describe the heat transfer fluid (HTF) consisting of a mixture of inorganic salts for use in concentrating energy applications. Previous commercially available molten salt heat transfer fluids have a high melting point, typically 140°C or higher which limits their commercial use due to the risk of freezing (Suite, 2010). From previous studies have also found molten salt as heat transfer fluid by exploiting behavior eutectic composition novel materials, has led to low melting point of 65 °C and the thermal stability limit over 500 °C. There are various types of salt are now available in large commercial quantities from several suppliers. There are several formulations commercially available salt, mixed with nitrate or nitrite sold under various brand. The molten salt component are always used based on nitrate are sodium nitrate (NaNO_3), sodium nitrite (NaNO_2), potassium nitrate (KNO_3), calcium nitrate ($\text{Ca(NO}_3)_2$)-tetrahydrated and lithium nitrate (LiNO_3).

Because of energy crisis nowadays, the utilization of low temperature waste heat draws more and more attention (Chen K *et al.*, 2014). The low temperature waste heat from solar thermal, geothermal, biomass, industrial and automobile, are among the potentially promising energy resources that capable to meet todays world energy demand (Salim, and Rafiq, 2012). Waste heat recovery through the application of Rankine cycle system is considered as an effective method of recovering the waste heat, as it aims to minimize the amount of heat wasted by the way of reusing it in either the same or a different process to produce a useful energy. Therefore, in this study, an alternative HTF based on inorganic salt will be introduced into the system in order to overcome the weakness of present molten salt HTF to applied in waste energy recovery. It is expected that the HTF exhibits both positive characteristics of HTF for example, lower melting point and high thermal stability.

1.2 Problem Statement

The lack of capability of heat transfer inside the cycle (evaporator) has led to ineffective operation of the cycle with generally small amount of recovered waste heat absorbed, and thus, small energy density is being generated by the system. Conventional approach to enhance the heat transfer by increasing the evaporator size

will increase the system cost. Alternatively, improving the heat transfer process by mean of using an appropriate heat transfer fluid based on molten salt is considered as effective with low cost. Using a molten salt as a heat transfer fluid also can deliver significant advantages over alternatives such as mineral oil. The performance of molten salt much higher compared than other organic oil. It can handle temperatures up to 550°C (Chhabara, 2010). However, from the previous study, HTF based on the molten salt have a high melting point typically up 240 °C and expensive and the main problem is the molten salts freeze at relatively high temperatures in the range of 120°C to 220°C (Chhabara, 2010). A lower melting point in range of 60 - 120 °C and a high thermal stability above 500 °C are desired. Because such a fluid would enhance the overall efficiency of the plants by utilizing less energy to keep salt in the liquid state and by producing superheated steam at higher temperatures in the Rankine cycle. Because of this restraint, the alternative heat transfer fluid will be introduced to overcome the HTF nowadays with used mixture inorganic salt based on nitrate.

1.3 Objective

Objective of this research is:-

- To prepare nitrates based molten salt compositions with different constituent salts.
- To characterize the physical and thermal properties of molten salt based on various salt compositions
- To determine best composition molten salt based nitrate which achieved a lower melting point and high thermal stability of heat transfer fluid.

1.4 Scope

This investigation will conducted to synthesis of molten salt as heat transfer fluid for waste heat recovery application are:-

- The mixture of molten salt based on nitrate salt.

- Binary, ternary and quaternary eutectic mixtures of these salts have been proposed for the lower melting point and high thermal stability of the heat transfer fluid,
- The binary salt mixture studied in this work are 46 wt% Sodium Nitrate (NaNO_3), 54 wt% Potassium Nitrate (KNO_3) and 45.8 wt% Lithium Nitrate (LiNO_3), 54.2 wt% Potassium Nitrate (KNO_3).
- For ternary salt mixture studied in this work are 56.4 wt% Potassium Nitrate (KNO_3), 24.1 wt% Sodium Nitrite (NaNO_2), 19.6 wt% Lithium Nitrate (LiNO_3) and 67.2 wt% Potassium Nitrate (KNO_3), 19.3 wt% Calcium Nitrate ($\text{Ca(NO}_3)_2$), 13.5 wt% Lithium Nitrate (LiNO_3).
- For quaternary salt mixture studied in this work are 40wt% Potassium Nitrate (KNO_3), 15wt% Sodium Nitrite (NaNO_3), 20wt% Lithium Nitrate (LiNO_3), 25wt% Calcium Nitrate ($\text{Ca(NO}_3)_2$)
- Characterization physical and thermal properties using some of analysis testing such as thermo gravimetric analysis (TGA) for the thermal stability, differential scanning calorimetry (DSC) will be observed the heat capacity and. Differential Thermal Analysis (DTA) will be measured the melting point.



PT TAA
PERPUSTAKAAN TUNKU AMINAH

CHAPTER 2

LITERATURE REVIEW

2.1 Introduction

For concentrated waste heat recovery system, the type of liquid heat carrier has a direct effect on this system. Using heat transfer fluid, electricity can be generated even when sunlight is not available. Some organic materials such as oil and inorganic materials such as molten salts have been proposed for use as a heat transfer fluid potential. Lack of capacity of the heat transfer in the cycle has led to the ineffectiveness of the operation cycle with a small amount of waste heat generally reabsorbed, and with it, a small energy density is generated by the system. For this reason the material used as the heat transfer fluid requires improvement in thermal stability associated with material properties (Villada *et al.*, 2014). By using organic liquid it cannot reach temperatures above 400°C with acceptable performance, because degradation into components that cannot be used at high temperatures. At temperatures above 400°C, the liquid becomes inoperative. Therefore, the temperature range is limited capping the overall efficiency of the steam cycle. Molten salt mixture was used to increase the energy conversion efficiency and reduce the cost of electricity production (Bauer, *et al.*, 2010). Several physical and thermodynamic properties of thermal energy play significant role in determining the efficiency and performance of waste heat recovery system. The three parameter which directly affect the thermal energy capacity in system are melting point, thermal stability and heat capacity where these parameter most important feature to consider in the system for heat transfer applications. From the previous literature there are large amount of melting point data available for various molten salt system with melting point less than 120 °C is very limited. From all the previous study on

molten salt system revealed that five group of molten salt are emphasized and commonly used alkaline nitrate/nitrite, carbonates, sulphates, chlorides and hydroxide.

2.2 Overview of Molten Salt and Applications

Components or compounds such as sodium nitrate salt can be written in general as M^+X^- where X^- is the anion and M^+ is a cation. In general, the selection of materials compatibility characteristics usually control the choice of anion for example fluoride, chloride, nitrate and so on. The option of cations usually controlled by other presentation issues such as the characterization of physical and thermal properties. Some examples of molten salt components are Beryllium fluoride (BeF_2), Magnesium chloride ($MgCl_2$), Sodium borohydride ($NaBF_4$) and Pottasium nitrate (KNO_3).

Salt mixture composed of different individuals salt components are mixed together into a multi-component system as a binary mixture, ternary mixtures or quaternary mixture. The melting point of the individual components should be high for any application. Mixing of several components to the system binaries, ternary or quaternary salt can reduces the melting point of the resulting system to a more practical level. Each mixture has a specific composition depends on the different parts of each component in the mixture. Each of the mixtures and compositions have physical properties and chemical different, and therefore the molten salt is optional depending on the type of application.

Applications of molten salt can be seen in thermal energy storage. Thermal energy storage (TES) has been designed to meet the power dispatchable load profiles with middle and high value benefits to utility power. The two groups of sensible heat storage are solid such as. concrete, rock, ceramics and for liquid like water and molten salt (Thomas Bauer, Breidenbach, & Eck 2010). Intermittent nature of solar energy is required in the TES system for the most efficient use of this energy source. TES system functioned as a reservoir of energy to collect and transfer the heat energy of Heat Transfer Fluid (HTF) for media storage. Thermal energy normally collected by the parabolic trough, then transferred to the storage of heat by heat transfer fluid and subsequently transferred to the steam generator storage media. To enable the storage of thermal energy in the system directly, the heat transfer fluid

will collect solar heat that serves as a storage medium. The cost of solar power systems is dependent on the properties of the heat storage medium and heat transfer fluids (Reddy, 2011).

Other research presented focused on molten salt storage for concentrated solar power plants. Molten salt is the best candidate because they have the advantage of a high heat capacity, high density, high thermal stability and low cost, and it is also known for its excellent heat transfer characteristics for use in thermal storage. This application has become important in the thermal technologies for solar energy concentration (Villada *et al.*, 2014). System using molten salt as the heat transfer fluid and for the thermal storage has been proposed for solar thermal power generation. The use of molten salt as the heat transfer fluid because it is cheaper, compact, and can store more energy per volume of oil-based HTFs. Additionally it also offers good storage conditions. The other advantages of the molten salt is i) pollute less, ii) not flammable, iii) more abundant iv) has a lower vapor pressure, v) offer cost savings due to smaller heat tank and pipes (Sniderman, 2012). Of the overall research on the various properties of the material, molten salt is a very special group that has great potential as thermal energy storage and heat transfer media for solar energy applications. Molten salt, on the other side can be used at high temperatures above 500 °C and it does not indicate one of the dangers and serious manner even have characteristics good heat transfer. Normally, salt used is a mixture of sodium and potassium nitrate and sodium nitrate, commonly referred to as a heat transfer fluid (Singh, 1985). Furthermore, molten salt is significantly less costly than the oil based HTFs currently used and allows for long term storage for heat.

Another application of molten salt is waste heat recovery. Waste heat can be interpreted as heat rejected from a facility to the environment. Recovery and reuse of this heat has the potential for reducing energy cost. Waste heat recovery system in which waste heat fluid, such as flue gasses, through a heat exchanger configured to transfer energy in the form of heat to the heat transfer fluid, preferably molten salt (Jeremy, *et al.*, 2010). Energy in molten salt is used to generate usable energy such as electricity. In other words, a waste heat recovery system, which consists of liquid waste heat sources where the first heat exchanger configured to transfer heat energy from waste liquid to liquid heat transfer while the second heat exchanger configured to transfer energy from the heat transfer fluid to the working fluid; and energy production system is configured to convert the energy transferred in the working

fluid into electrical energy (Jeremy, Xie, & Safe, 2010). Figure 2.1 shows the molten salt system as heat transfer fluid.




Figure 2.1 Molten salt system (Jeremy, *et al.*, 2010).

2.3 Melting Point

2.3.1 Melting point for various salt

From the previous researcher, there are large amount of melting point data available for various molten salt system. From the previous also, it was found those with melting point less than 120 °C is very limited. All the previous study on molten salt system revealed that five group of molten salt are commonly used. That is alkaline nitrates, carbonates, sulphates, chlorides and hydroxide. Nowadays focuses on expanding the database of thermophysical properties of alkali and alkaline earth cations with nitrate or nitrite anions. Previous reports discuss low-melting salts containing lithium, sodium, potassium and calcium cations with nitrate and nitrite anions. The main method of thermal decomposition of these nitrate salt was agreed by many researchers such as Freeman (1956) and Sirotkin (1959). Recent developments in multi-component molten salt consisting of alkali and alkaline earth nitrates have the appropriate characteristic to be applied as heat transfer fluid in

waste heat recovery system. The melting points of individual and multi components nitrate/nitrite system are listed in Table 2.1 (Peng, *et al.*, 2010).

Table 2.1 Melting point of various nitrate salt systems (Peng, *et al.*, 2010).

Compound	Melting point (°C)
LiNO ₃	253
NaNO ₃	307
KNO ₃	334
Ca(NO ₃) ₂	561
Sr(NO ₃) ₂	570
Ba(NO ₃) ₂	590
NaNO ₃ -NaNO ₂	221
NaNO ₃ -NaNO ₂ -KNO ₃	141
NaNO ₃ -KNO ₃ -CaNO ₃	133
LiNO ₃ -KNO ₃ -NaNO ₃	120
KNO ₃ -CaNO ₃ -LiNO ₃	117
LiNO ₃ -KNO ₃ -NHNO ₃	92
KNO ₃ -NHNO ₃ -AgNO ₃	52
LiNO ₃ -NaNO ₂ -NaNO ₃ -KNO ₃	99

Different from the nitrate salt, for carbonate system that list in Table 2.2 (Peng, *et al.*, 2010) the melting point for both the individual and multi component carbonate system are on the higher side. For this carbonate system, lowest melting point was achieved with lithium, sodium and potassium ternary system where the melting point is 277 °C that is higher than nitrate ternary system with the same cation (Marionwski & Maru, 1977). Caused by thermal decomposition issues, the selection of components for the carbonate system is very limited and some salt like CaCO₃ doesn't have stable form at high temperature and the lack of multi-component system reduces the chance of the synthesis of low melting point salt mixtures. Although this group is not stable salt heat and working temperature range is relatively small, but it is still seen as the candidate can work at a high temperature because of low prices.

Table 2.2. Melting point of various carbonate salt systems (Peng, *et al.*, 2010)

Compound	Melting Point (°C)
Li ₂ CO ₃	732
Na ₂ CO ₃	858
K ₂ CO ₃	900
MgCO ₃	990
Na ₂ CO ₃ -K ₂ CO ₃	710
Li ₂ CO ₃ -Na ₂ CO ₃	496
Li ₂ CO ₃ -K ₂ CO ₃	488
Li ₂ CO ₃ -K ₂ CO ₃ -Na ₂ CO ₃	397

Alkali and alkaline fluoride/chloride salts are also selected as one possible choice as heat transfer fluid in solar energy and the melting point from the previous literature are given in Table 2.3 (Mayo, 1971). A lot of study has been done for this molten salt group and found that the melting point for this group is the same range with carbonate group but for the pure salt, metal chloride salt have a low

Table 2.3 Melting point of various fluoride/chloride salt systems (Mayo, 1971).

Compound	Melting Point (°C)
LiF	849
NaF	996
KF	858
LiCl	610
NaCl	801
KCl	771
LiF-KF	493
LiF-NaF	652
LiCl-KF	487
LiF-NaF-KF	454
LiF-NaF-KF-MgF ₂	449
LiF-KF-BaF ₂	320
LiF-KF-CsF-RbF	256

2.3.2 Melting temperature for molten salt based on nitrate/nitrite system

Application molten salt as the heat transfer fluid is considered by the lower temperature limit and is determined by the melting temperature. The main challenge with molten salt is to be frozen during the operation. Therefore alkali nitrate and nitrite is a good candidate because of the low melting and excellent heat capacity. Nitrate salts were selected for use because of their favorable properties compared with other candidates. Commercially, molten salt heat transfer fluid previously found to have a high melting point, typically 140 °C or more. The liquid molten salt compositions include novel materials which consist of a mixture of lithium nitrate salts, sodium, potassium, cesium, and calcium. This unique mix can exploit eutectic behavior and cause the low melting at 65 °C and the thermal stability limit over 500 °C (Raade & Padowitz, 2011). Several molten salt heat transfer fluids have been used for solar thermal systems. Table 2.4 shows a systematic list of the melting temperature of single salt and the minimum melting temperature of salt system with cations calcium (Ca), potassium (K), lithium (Li), and sodium (Na) and the anions

nitrate (NO_3) and nitrite (NO_2) using previous sources (Bauer, Laing, & Tamme, 2011).

Table 2.4 Matrix of (minimum) melting temperature of subsystems of the reciprocal system Ca,K,Li,Na/ NO_2 , NO_3 (Bauer, *et al.*, 2011)

	NO_2	NO_3	NO_2 , NO_3
Single salt and binary system with common action			
Ca	398°C#	561°C#	393°C
K	440°C	334°C	316-323°C
Li	220°C	254°C	196°C
Na	275°C	306°C	226-233°C
Binary systems with common anion and ternary reciprocal)			
Ca,K	185°C	145-174°C	130°C
Ca,Li	205-235°C	235°C	178°C
Ca,Na	200-223°C	226-230°C	154°C
K,Li	98°C	126°C	94°C
K,Na	225°C	222°C	142°C
Li,Na	151°C	196°C	126°C
Ternary additive common anion and quaternary reciprocal			
Ca,K,Li	N/A	117°C	N/A
Ca,K,Na	N/A	130°C	N/A
Ca,Li,Na	N/A	170°C	N/A
K,Li,Na	N/A	119°C	N/A
Quaternary additive common anion and quinary reciprocal			
Ca,K,Li,Na	N/A	109°C	N/A

Decomposition at melting temperature

Based on the table above the melting temperature of the single salt is between 220 °C (LiNO_2) to 561 °C ($\text{Ca}(\text{NO}_3)_2$). Compared to single salt, more salt mixture showed the advantages of lower melting temperature. Therefore, a mixture of salt may have a wider temperature range than a single salt.

2.4 Heat capacity

For heating process, the temperature of molten salt increase by absorbing energy a substance to the substance's increase in temperature. Conversely, in the cooling process, which is the same as the amount of heat released or used in the development of heating systems. In other words, heat capacity is the amount of heat required to increased the temperature of certain material by 1 °C and for large heat capacity assures the efficiency of the application.

2.4.1 Heat capacity for various salt

From the previous researcher, the heat capacity alkali/alkaline nitrate was investigated for both individual and multi-component system to simplify the comparison, between various type of salt the heat capacity value to differentiate the various salt as heat transfer fluid and shown in the following table. Among those alkali nitrate salt system it shown that LiNO_3 has a large heat capacity while KNO_3 present the lowest value. It can be seen in Table 2.5 which shown the heat capacity result for various compound of salt.

Table 2.5 Heat capacity of various nitrate salt systems (Marianowski & Maru, 1977)

Compound	Heat capacity (J/g.K)
LiNO_3	2.175
NaNO_3	1.686
KNO_3	1.400
$\text{NaNO}_3\text{-KNO}_3$	1.533
$\text{LiNO}_3\text{-KNO}_3$	1.642
$\text{LiNO}_3\text{-KNO}_3\text{-NaNO}_3$	1.681
$\text{LiNO}_3\text{-NaNO}_2\text{-NaNO}_3\text{-KNO}_3$	1.689

Completely different with carbonate salt system, the heat capacity is almost constant and independent with temperature (Marianowski & Maru, 1977). For pure carbonate salt, the heat capacity shown decrease, which means the value for lithium carbonates is largest and potassium carbonates is smallest. It can seen in Table 2.6 the result of heat capacity value for carbonate salt. The value of heat capacity for carbonate salt when melt is larger than solid state but when carbonate in binary system the value of heat capacity in solid is larger than liquid state (Wang, 2011).

Table 2.6 Heat capacity of various carbonate salt systems (Marianowski & Maru, 1977)

Compound	Heat capacity (J/g.K)
Li_2CO_3	2.50
Na_2CO_3	1.78
K_2CO_3	1.51
$\text{Na}_2\text{CO}_3\text{-K}_2\text{CO}_3$	1.57
$\text{Li}_2\text{CO}_3\text{-K}_2\text{CO}_3$	1.60
$\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$	2.09
$\text{Li}_2\text{CO}_3\text{-K}_2\text{CO}_3\text{-Na}_2\text{CO}_3$	1.63

Besides carbonate and nitrate, the study of fluoride/chloride was also studied by previous researcher as Takahashi (1985) to compared with other types of salt available. The value for heat capacity fluoride/chloride shown in Table 2.7. Same with carbonate salt system, the value of heat capacity shown the salt contain lithium halide have a biggest capacity compared than pottasium halide is smallest. This fluoride/chloride salt have smallest value in liquid state.

Table 2.7 Heat capacity of various fluoride/chloride salt systems (Takahashi, 1985)

Compound	Heat capacity (J/g.K)
LiCl	1.48
NaCl	1.15
KCl	0.90
LiF-KF	1.63
NaCl-MgCl ₂	1.00
LiF-NaF-KF	1.55
KCl-MgCl ₂ -CaCl ₂	0.92
LiF-NaF-KF-MgF ₂	1.55

In summary, based on the various salt above the molten salt based on nitrate shown the high capacity compared than carbonate, fluoride/chloride including pure salt, binary salt, ternary salt or quaternary. Molten nitrate salt is suitable to applied as heat transfer fluid in any application.

2.5 Thermal stability for various salt

The general finding that molten salt mixture based on nitrate is stable up to temperature 500 °C. This advanced HTF developed as a result of the discovery process in which a mixture of materials inspection nitrate salts have low melting points and are stable at temperatures of at least 500 °C based on the properties, including the composition, melting point, and thermal stability (Suite, 2010). The thermal decomposition processes of nitrates and nitrites were summarized by Stern, (2010). From previous review the thermal stability of the salt was detemined by using thermal gravimetric analysis (TGA). The decomposition temperature depends on various aspects include the definition itself, the experimental method (e.g. sensitivity, heating rate), crucible material and atmosphere. Figure 2.2 show results of TGA of single nitrate and nitrite salts, as well as four mixtures with a low melting temperature (Bauer *et.al.*, 2010.)

REFERENCES

- Alexander, J. H. (1947). Phase Relations in Heat Transfer Salt systems. *Industrial & Engineering Chemistry* 39(8) , 1044-1049
- Bauer, T., Laing, D., and Tamme, R., (2010). Overview of PCMs for concentrated solar power in the temperature range 200 to 350 °C. *Advances in Science and Technology* , vol 272-277.
- Bauer, T, Laing D, and Tamme R. (2011). "Recent Progress in Alkali Nitrate / Nitrite Developments for Solar Thermal Power Applications.",1–10.
- Bauer, Breidenbach N, and Eck,M (2011). "Overview Of Molten Salt Storage Systems And Material Development For Solar Thermal Power Plants." : 1–8.
- Bergman, A. (1955). unknown title (Russian) Izvest. Sektora Fiz.Khim Anal. *Akad. Nauk S.S.S.R* , 156.
- Berg, R.W., and Kerridge, D.H. (2004). The NaNO₃/KNO₃ system: the position of the solidus and subsolidus. *Dalton Transactions*,vol 2224-2229.
- Bradshaw and Siegel. (2009). "Development of molten nitrate salt mixtures for concentrating solar power system". *proc.SolarPACES*, (p. no.1158). Berlin,Germany
- Bradshaw, R. (1990). High-temperature stability of ternary nitrate molten salts for solar thermal energy systems. *Solar Energy Materials*, vol 51-60.
- Carvalho, G.D.,Frollini, E., and Santos, N.D., (1996) Thermal conductivity of polymers by hot- wire method, *J. Appl. Poly. Sci.*, 62, 2281-2285.
- ChanC.W., Ling-Chin J., Roskilly,A.P. (2013). A review of chemical heat pumps, thermodynamic cycles and thermal energy storage technologies for low grade heat utilization. *Appl Therm Eng*, 50, pp. 1257–1273.
- Chen K., Wang J.,Dai Y. and Liu Y. (2014). Thermodynamic Analysis of a Low Temperature Waste Heat Recovery System Based on the Concept of Solar Chimney. *Energy Conversion and Management*, 80(0) p 78-86.
- Chhabara, R. (2010, February 4). *CSP Today*. Retrieved November 18, 2014, from Turning up the heat: Molten salt as a heat transfer fluid:

<http://social.csptoday.com/technology/turning-heat-molten-salt-heat-transfer-fluid>

Cordaro, J.G., Rubin, N.C., and Bradshaw. R.W. (2011). Multi component mixture based on nitrate/nitrite anions. *Journal of Solar Energy Engineering* 133, 011014-1-011014-4.

Cordaro, J.G., Rubin, N.C., (2010) Multi-component molten salt mixtures based on nitrate/nitrite anions *Solar PACES* p7.

Fernández, A.G., Lasanta, M.I., Perez, F.J., (2012) Molten salt corrosion of stainless steels and low-Cr steel in CSP plants, *Oxid. Met.* 78 (5-6) 329–348

Fernandez, A.G., Galleguillos, H., Fuentealba, E., Perez1, F.J., (2014) Thermal characterization of HITEC molten salt energy storage in solar linear concentrated energy, *J. Therm Anal Calorim*

Freeman, E. (1956). The kinetics of the thermal decomposition of sodium nitrate and of the reaction between sodium nitrite and oxygen. *Journal of Physical Chemistry* 60 (11) , 1471–1600

Heidi S.Nygard and Olsen E. (2012). Review of Thermal Processing of Biomass. *International Journal of Low-Carbon Technologies Advance Access*.

Hermann, U., Kelly, B., Price, H., (2004). Two tank molten salt storage for parabolic trough solar power plant. *Energy* 29, 883-893.

Hung. T.C, Shai. T.C, Wang. S.K (1997). A review of organic Rankine cycles (ORCs) for the recovery of low-grade waste heat. *Energy*, 22, pp. 661–667.

Ichikawa K., Matsumoto T. (1983) Heat capacities of lithium, sodium, potassium, rubidium, and caesium nitrates in the solid and liquid states - Bulletin of the Chemical Society of Japan, 56(7)

Jänecke, E. (1942). The quaternary system Na,K,Ca,Mg // NO₃ and its subsystems. *Elektrochemie und angewandte physikalische Chemie* , 453-512.

Jagadees.S. (2011, July 28). *Alienate World*. Retrieved November 18, 2014, from Wordpress.com: <https://jagadees.wordpress.com/2011/07/28/advantages-of-using-molten-salt>

Jriri T., Rogez J., Bergman C., Mathieu J. C. (1995) Thermodynamic study of the condensed phases of NaNO₃, KNO₃ and CsNO₃ and their transitions *Thermochimica Acta*, 266(C), 147-161

Jeremy A.,Xie Q., and Safe P. (2010). *Patent No. WO2010138597A3*. United States.

Kearny, D. Kelly,B. Cable, R ,Potrovizta, N. (2002). Assesment of a molten salt heat transfer fluid in a parabolic through solar field. *Submission to JSSE*.

- Kearney, D., Mahoney, R., (2002) Assessment of a molten heat transfer fluid in a parabolic trough solar field, *Sol. Energy Eng.* 12
- Kramer, C.M., Wilson, C.J., (1980) The phase diagram of $\text{NaNO}_3\text{-KNO}_3$. *Thermochimica Acta*, 42,p253-264
- Kolb, G. (1992). Development of a control algorithm for a molten salt solar center receiver in a cylindrical configuration. *solar engineering*, 5-9.
- Laue, W.(1998). *Nitrates and Nitrites*, in *Ullmann's Encycl. of Industrial Chemistry* 6. Edition.
- Levin, E.M., Robbins, C.R., McMurdie, H.F.,(1964) *Phase diagrams for ceramists* American Ceramic Society, American Ceramic Society, Columbus, Ohio
- Lin, P.L., Pelton, A. D., and Bale, C. W., (1979) "Computation of ternary molten salt phase diagrams," *J. American Ceramic Soc.*, vol. 62, no. 7-8, pp. 414-422.
- Marianowski, L.G., and Maru, H.C.,(1977) Latent heat thermal energy storage systems above 450.8°C , Proceedings of 12th intersociety energy conversion engineering conference, 55- 66
- Mayo, K.E., (1971) Heat source systems, USA Patent 3605720.
- Menzies, A.W.C.and Dutt, N.N. . (1911). The Liquidus Surface of the Ternary System Composed of the Nitrates of Potassium, Sodium, and Calcium. *Journal of the American Chemical Society* , 1366-1375.
- Paulik J, Paulik F, Arnold M. (1983) Thermogravimetric examination of the dehydration of calcium nitrate tetrahydrate under quasi-isothermal and quasi-isobaric conditions. *J Therm Anal*;27:409–18
- Peng, Q., Ding, J., Wei, X., Yang, J., and Yang, X.,(2010) The preparation and properties of multi- component molten salts, *Applied Energy*, 87, 2812-2817
- Prigogine, I., Defay, R., (1973) *Chemical Thermodynamics..* Longman Group Limited, London, pp.177-178.
- Raade, J., Padowitz, D., (2011) Development of molten salt heat transfer fluid with low melting point and high thermal stability, *J. Solar Eng.* 33, 031013- 1–031013-6.
- Reily, H.R. and Kolb, G. (2011). An evaluation of molten salt power towers including result of the solar two project. SAND2011-3674.
- Reddy, R. G. (2011). Molten salt applications. *Journal of Phase Equilibria and Diffusion* Vol. 32 No. 4

- Salim, R.A, and Rafiq, S. (2012). Why Do Some Emerging Economies Proactively Accelerate the Adoption of Renewable Energy. *Energy Economics*, 34(4) p1051-1057.
- Singh. (1985). *Heat Transfer Fluids and Systems for Process and Energy Applications*. United States, America: CRC Press.
- Sirotkin, G. (1959). Equilibrium in melts of the nitrates and nitrites of sodium potassium. *Russian Journal of Inorganic Chemistry* 4 (11) , 1180–1184.
- Sniderman, D. (2012, February). *ASME.org*. Retrieved November 16, 2014, from <https://www.asme.org/engineering-topics/articles/heat-transfer/salt-heat-transfer-fluids-in-csp>
- Speidel P., Kelly, B., Prairie,M., Pachecho, J., Gilbert, R., Reilly, H. Performance of the Solar Two Central Receiver Power Plant. *Preprint of the 9th International Symposium Solar Thermal Symposium on Solar Thermal Concentrating Technologies*. Odiello,France.
- Stern, K. (2010). High Temperature Properties and Thermal Decomposition of Inorganic Salts with Oxyanions. *CRC-Press*.
- Suite, St (2010). “Development Of Molten Salt Heat Transfer Fluid With Low Melting Point And High Thermal Stability.” 1(510).
- Takahashi, Y., (1985) Latent heat measurement by DSC with sapphire as standard material, *Thermochim Acta*, 88(1), 199-204.
- Villada, C *et al.* 2014. “Thermal Evaluation of Molten Salts for Solar Thermal Energy Storage.” (12): 1–4.
- W.Raade J. and Padowitz D. (2011). Development of Molten Salt Heat Transfer Fluid With Low Melting Point and High Thermal Stability. *Journal of Solar Energy Engineering* 133(3), 031013 , 1-6.
- Wang, T., Mantha D, and Ramana G.R (2012). “Thermal Stability of the Eutectic Composition in LiNO₃–NaNO₃–KNO₃ Ternary System Used for Thermal Energy Storage.” *Solar Energy Materials and Solar Cells* 100: 162–68. <http://linkinghub.elsevier.com/retrieve/pii/S0927024812000104> (December 6, 2014).
- Wang, T., (2011). “High Themal Energy Storage Density Molten Salts For Parabolic.”

- Wang, T., Mantha, D. and Ramana G.R. (2013). Novel low melting point quaternary eutectic system for solar thermal energy storage. *Applied energy* 102 , 1422-1429.
- Zhang, X., Tian, J., Xu, K., Gao, Y. (2003). Thermodynamic evaluation of phase equilibria in $\text{NaNO}_3\text{-KNO}_3$ system. *J. of Phase Equil. and Diffusion* 24 , 441-446.

